



CARBOWAX™ Polyethylene Glycol 8000 Flake (Inhibited)

Product Description

CARBOWAX™ Polyethylene Glycol (PEG) 8000 Flake is a hard, waxy solid having the appearance of thin, irregularly shaped shards. The flake thickness is slightly variable within a range of approximately 0.02 – 0.07 inches. CARBOWAX™ PEG 8000 Flake is chemically equivalent to its spherical granular counterpart, being produced from the same molten material manufactured at The Dow Chemical Company's St. Charles Operations (Taft) plant for CARBOWAX™ PEGs in Hahnville, LA. Owing to the lower surface area as compared to the granular form, the flaked grade exhibits longer relative dissolution times in water-based applications. This material contains the added stabilizer, BHT, at a nominal concentration of 100 PPM.

Typical Physical Properties – CARBOWAX PEG 8000 ⁽¹⁾

Range of Avg. Molecular Weight	Range of Average Hydroxyl Number, mg KOH/g	Liquid Density g/cc			Melting or Freezing Range, °C	Solubility in Water at 20°C, % by wt
		20°C	70°C	90°C		
7000-9000	12-16	Solid	1.0852	1.0689	55-62	63

Viscosity at 100°C, cSt	Average Number of Repeating Oxyethylene Units	Surface Tension at 25°C mN/m, 50% Aqueous Solution	Heat of Fusion, Cal/g	Heat of Combustion (h) at 25°C, Btu/lb (J/g)	CFTA/INCI Nomenclature
470 - 900	181.4	51.3	41	-11,410 (-26,521)	PEG-180

⁽¹⁾ Typical properties, not to be construed as specifications.

Product Stewardship

Dow encourages its customers and potential users to review their applications from the standpoint of human health and environmental aspects. To help ensure that Dow products are not used in ways for which they are not intended or tested, Dow personnel will assist customers in dealing with environmental and product safety considerations. Dow literature, including material Safety Data Sheets, should be consulted prior to the use.

For More Information

North America: toll-free 1-800-447-4369
fax 1-989-832-1465

Europe: toll-free +800 3 694 6367
call +32 3 450 2240
fax +32 3 450 2815

Pacific: toll-free +800 7776 7776
call +60 3 7958 3392
fax +60 3 7958 5598

Latin America: call +55 11 5188 9222
fax +55 11 5188 9749

<http://www.carbowax.com>

NOTICE: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

